















technical specifications



TECHNICAL SPECIFICATIONS	STANDARDS	TEST RESULT	TECHNICAL SPECIFICATIONS	STANDARDS	TEST
 Size	EN 14617-16	1500 x 3365 mm	 Deep abrasion resistance	EN 14617-4	25,5
 Thickness	EN 14617-16	12 - 20 - 30 mm	 Frost resistance	EN 14617-5	Resis
 Specific weight	EN 14617-1	2,4 kg/dm ³	 Fire reaction	EN 13501-1	A1
 Flexural strength	EN 14617-2	53 N/mm ²	 Resistance to acids and bases	EN 14617-10	C4 -
 Water absorption	EN 14617-1	0,1%	 Colour resistance to light	DIN 51094	No of colour
 Resistance to compression	ASTM C773	230-250 N/mm ²	 Coefficient of linear thermal expansion	EN 14617-11	6,3 x
 Impact resistance	EN 14617-9	3,3 Joule sample: 20 mm thick	 Thermal conductivity	EN ISO 10456	1,3 W